

品番	色記号	ページ	機能	価格 (円/m)	価格 (円/m ²)	有効巾 (cm)	柄リポート	防災認証	組成	重量 (g/m ²)	堅牢度		洗濯		ドライクリーニング A-1法		ウオッシュャブル 寸法変化率 (%)	赤外線カット率 IR (%)	紫外線カット率 UV (%)	洗濯表示
											耐光	耐光	洗濯 変退色	汚染 綿	変退色	汚染				
TPS-703	BL	P6	masa	5,800	3,860	150	タテ61.0cm×ヨコ147.0cm	A2180342	ポリエステル100%	68	3-4	4-5	4-5	4-5	4-5	タテ-0.8 ヨコ-0.5	66.6	73.6		
TPS-704	CHI	P4	masa	5,800	3,860	150	タテ61.0cm×ヨコ147.0cm	A2180342	ポリエステル100%	68	4	4	4-5	4-5	4-5	タテ-0.8 ヨコ-0.5	67.8	74.1		
TBO-001	GR	P20	masa	7,100	4,730	150	タテ63.5cm×ヨコ50.0cm	A2120180	ポリエステル100%	57	4以上	4-5	4-5	4-5	4-5	タテ-0.5 ヨコ-0.8	68.6	79.0		
	OR										4以上	4-5	4-5	4-5	4-5		68.1	79.4		
TBO-002	OR	P22	masa	7,100	4,730	150	タテ31.0cm×ヨコ25.0cm	A2120180	ポリエステル100%	48	4以上	4-5	4-5	4-5	4-5	タテ-0.8 ヨコ-0.4	58.7	68.7		
	LGRN										4以上	4-5	4-5	4-5	4-5		60.8	69.3		
	NA										4以上	4-5	4-5	4-5	4-5		61.5	66.1		
	R										4以上	4-5	4-5	4-5	4-5		54.6	61.7		
TBO-003	BE	P18	masa	7,100	4,730	150	タテ62.0cm×ヨコ75.0cm	A2120180	ポリエステル100%	45	4以上	4-5	4-5	4-5	4-5	タテ-0.4 ヨコ-0.2	53.7	60.2		
	NA										4以上	4-5	4-5	4-5	4-5		55.2	60.3		
	LGY										4以上	4-5	5	5	5		60.0	63.3		
TBO-005	OR	P24	masa	7,100	4,730	150	タテ30.0cm×ヨコ25.0cm	A2120180	ポリエステル100%	45	4以上	4-5	4-5	5	5	タテ-0.7 ヨコ-0.0	63.9	71.6		
	BK										4以上	4-5	4-5	5	4-5		67.2	74.2		
	LGY										4以上	4-5	5	5	5		56.6	63.1		
TBO-006	GO	P19	masa	7,100	4,730	150	タテ30.0cm×ヨコ12.5cm	A2120180	ポリエステル100%	42	4以上	4-5	4-5	5	5	タテ-0.8 ヨコ-0.2	59.8	66.7		
	BR										4	4-5	4-5	5	5		60.2	70.4		
	LGY										4以上	4-5	5	4-5	5		49.9	52.4		
TBO-007	R	P21	masa	7,100	4,730	150	タテ15.0cm×ヨコ25.0cm	A2120180	ポリエステル100%	33	4	4-5	4-5	5	5	タテ-0.5 ヨコ-0.2	50.5	59.8		
	GRN										4以上	4-5	4-5	5	5		50.6	56.9		
	LGY										4	4-5	5	5	5		62.6	69.0		
TBO-008	GO	P23	masa	7,100	4,730	150	タテ59.5cm×ヨコ75.0cm	A2120180	ポリエステル100%	49	4以上	4-5	4-5	5	5	タテ-0.5 ヨコ-0.3	62.6	69.6		
	GRN										4	4-5	4-5	5	5		61.5	69.5		
	BE										4以上	4-5	5	5	5		62.0	69.1		
TBO-009	BR	P25	masa	7,100	4,730	150	タテ30.0cm×ヨコ37.5cm	A2120180	ポリエステル100%	43	4以上	4-5	4-5	5	5	タテ-0.5 ヨコ-0.3	61.1	71.5		
	PUR										4	4-5	4-5	5	5		62.0	70.9		
	GRN										3-4	4-5	4-5	4-5	4-5		68.2	74.8		
TBO-010	OR	P17	masa	7,100	4,730	139	タテ15.5cm×ヨコ15.0cm	A2180294	ポリエステル100%	48	4	4-5	4-5	4-5	4-5	タテ-0.3 ヨコ-0.2	65.6	70.8		
	GY										3	4-5	4-5	4-5	4-5		66.1	71.6		
	LBE										3-4	4-5	4-5	4-5	4-5		68.2	74.7		
	OCH										3-4	4-5	4-5	4-5	4-5		67.0	74.0		
	TC										3-4	4-5	4-5	4-5	4-5		69.3	79.9		
TBO-011	CR	P14	masa	7,100	4,730	147.5	タテ2.0cm×ヨコ3.3cm	A2180294	ポリエステル100%	42	4	4-5	4-5	4-5	4-5	タテ-0.7 ヨコ-0.2	69.3	76.3		
	GY										3-4	4-5	4-5	4-5	4-5		70.1	78.7		
	LOV										3-4	4-5	4-5	4-5	4-5		68.0	75.7		
	MS										3-4	4-5	4-5	4-5	4-5		68.7	78.7		
	LBE										3-4	4-5	4-5	4-5	4-5		67.0	73.0		
TBO-012	CR	P12	masa	7,100	4,730	148.5	タテ30.0cm×ヨコ37.0cm	A2180294	ポリエステル100%	48	4	4-5	4-5	4-5	4-5	タテ0.0 ヨコ-0.2	55.0	60.1		
	BL										3-4	4-5	4-5	4-5	4-5		68.9	75.5		
	TC										3-4	4-5	4-5	4-5	4-5		68.3	76.7		
	MS										3	4-5	4-5	4-5	4-5		70.8	78.3		
	LBR										3-4	4-5	4-5	4-5	4-5		71.1	82.4		
TBO-013	CR	P16	masa	7,100	4,730	148	タテ30.0cm×ヨコ74.0cm	A2180294	ポリエステル100%	44	4	4-5	4-5	4-5	4-5	タテ-0.2 ヨコ0.0	74.0	80.2		
	GY										3	4-5	4-5	4-5	4-5		60.9	67.0		
	LBE										3-4	4-5	4-5	4-5	4-5		71.1	76.8		
	GRN										3	4-5	4-5	4-5	4-5		71.1	78.7		
	TC										4	4-5	5	4-5	5		76.1	84.4		
TC-003	NA	P38	masa	9,600	3,200	300	タテ0.0cm×ヨコ0.0cm	A0100412	ポリエステル100%	48	4	4-5	5	4-5	5	タテ0.0 ヨコ-0.3	76.1	84.4		
	OR										4以上	4-5	4-5	—	—		58.4	64.9		
	Y										4以上	4-5	4-5	—	—		56.5	62.5		
	GRN										4以上	4-5	4-5	—	—		55.6	62.3		
	BL										4以上	4-5	4-5	—	—		60.8	67.1		
TC-006	NA	P29	masa	5,250	3,500	150	タテ0.0cm×ヨコ0.0cm	A0090399	ポリエステル100%	130	4以上	5	5	5	5	タテ-1.8 ヨコ-0.6	60.4	65.9		
	IVY										4以上	4-5	4-5	—	—		53.6	60.1		
	PI										4以上	4-5	4-5	—	—		59.8	65.4		
	NA										4以上	5	5	5	5		59.7	65.2		
	IVY										4以上	4-5	5	—	—		60.9	67.8		
TC-007	Y	P37	masa	10,500	3,500	300	タテ0.0cm×ヨコ1.3cm	A0100005	ポリエステル100%	114	4以上	4-5	4-5	—	—	タテ-0.3 ヨコ-1.0	64.9	72.4		
	NA										4以上	4-5	5	5	5		60.8	67.6		
	IVY										4以上	4-5	4-5	—	—		59.4	64.4		
	Y										4以上	4-5	4-5	—	—		52.0	56.3		
TC-008	NA	P31	masa	5,250	3,500	150	タテ0.0cm×ヨコ0.0cm	AO100006	ポリエステル100%	97	4以上	4-5	5	—	—	タテ-1.7 ヨコ-1.5	56.8	62.2		
	GR										4以上	4-5	4-5	—	—		49.6	55.6		
	LY										4以上	4-5	4-5	—	—		52.1	56.3		
	OR										4以上	4-5	4-5	—	—		47.9	53.4		
	DBR										4	4-5	5	4-5	5		49.4	54.6		
TC-009	NA	P36	masa	9,600	3,200	300	タテ0.0cm×ヨコ0.0cm	AO100188	ポリエステル100%	38	4	4-5	5	—	—	タテ-0.5 ヨコ-0.5	46.5	55.0		
	GR										4	4-5	5	—	—		51.2	58.4		
	LY										4	4-5	5	—	—		47.0	52.7		
	OR										4	4-5	5	—	—					
	DBR										4	4-5	5	—	—					
TC-010	NA	P26	masa	4,800	3,200	150	タテ0.0cm×ヨコ0.0cm	A0090426	ポリエステル100%	93	4	4-5	5	—	—	タテ-0.7 ヨコ-0.5				
	Y										4	4-5	5	—	—					
	LY										4	4-5	5	—	—					
	DGR										4	4-5	5	—	—					
	DBR										4	4-5	5	—	—					
NA	4以上	5	5	5	5															



TC-013	DBR	P39	masa	4,450	2,970	150	タテ0.0cm×ヨコ0.0cm	A2180352	ポリエステル100%	22	4以上	4-5	4-5	—	—	タテ-0.5 ヨコ-1.0	34.8	42.8
	OR										4以上	4-5	4-5	—	—		38.6	43.7
	R										4以上	4-5	4-5	—	—		37.7	42.6
	BK										4以上	4-5	4-5	—	—		38.2	44.3
	NA										4	4-5	5	4-5	5		36.7	40.2
TC-014	DGR	P35	masa	10,500	3,500	300	タテ0.0cm×ヨコ0.0cm	A2180357	ポリエステル100%	45	4以上	4-5	4-5	4-5	—	タテ-0.5 ヨコ-0.6	64.9	71.8
	R										4以上	4-5	4-5	4-5	—		53.9	60.4
	DBR										4	4-5	4-5	4-5	—		60.1	68.5
	BE										4	4-5	4-5	4-5	—		61.5	67.3
	NA										—	—	—	—	—		63.6	69.6
TC-015	GY	P28	masa	3,500	2,330	140	タテ0.0cm×ヨコ0.0cm	—	ポリエステル100%	32	4以上	4-5	5	4-5	5	タテ-0.0 ヨコ0.3	54.2	61.5
	PN										4以上	4-5	4-5	4-5	4-5		54.2	61.5
	BE										4	4-5	4-5	4-5	4-5		54.2	61.5
	GN										4以上	4-5	4-5	4-5	4-5		54.2	61.5
TC-019	BE	P24	masa	9,800	3,260	300	タテ0.0cm×ヨコ0.0cm	A2160502	ポリエステル100%	166	4以上	4-5	5	4-5	5	タテ-1.0 ヨコ-0.3	61.0	61.2
	BR										4以上	4-5	4-5	4-5	5		56.3	59.8
	NA										4以上	4-5	4-5	4-5	5		57.6	60.0
TC-020	BE	P32	masa	5,000	3,330	150	タテ0.0cm×ヨコ0.0cm	A2160540	ポリエステル100%	150	4以上	4-5	5	4-5	5	タテ-0.5 ヨコ0.2	61.1	60.4
	GRN										4以上	4-5	5	4-5	5		58.7	64.9
	NA										4以上	4-5	5	4-5	5		60.9	62.7
TC-021	BL	P33	masa	5,000	3,330	150	タテ8.5cm×ヨコ8.5cm	A2160505	ポリエステル100%	86	4以上	4-5	4-5	4-5	5	タテ-0.5 ヨコ0.1	59.0	68.8
	LBR										4以上	4-5	4-5	4-5	5		57.9	68.9
	NA										4以上	4-5	5	4-5	5		58.6	62.0
TC-022	LGY	P10	masa	4,800	3,200	150	タテ0.0cm×ヨコ0.0cm	A2180342	ポリエステル100%	68	4	4-5	4-5	4-5	4-5	タテ-0.8 ヨコ-0.5	67.8	74.1
	GY										4	4-5	4-5	4-5	4-5		66.9	73.5
	LBE										3-4	4-5	4-5	4-5	4-5		67.1	73.5
	PI										4	4-5	4-5	4-5	4-5		66.4	72.5
	MAS										3-4	4-5	4-5	4-5	4-5		66.5	72.6
	GO										3-4	4-5	4-5	4-5	4-5		66.4	74.3
	EM										3-4	4-5	4-5	4-5	4-5		67.5	75.1
	GN										3-4	4-5	4-5	4-5	4-5		66.0	73.4



※耐光堅牢度は色の面(部屋側)からの値で裏(日光)面からの照射では4級です

品番	色記号	ページ	機能	価格 (円/m)	価格 (円/㎡)	有効巾 (cm)	柄リポート	防災認証	組成	重量 (g/㎡)	堅牢度	洗濯		ドライクリーニング A-1法		ウォッシュブル	遮光等級	洗濯表示						
											耐光	洗濯	汚染	変退色	汚染	寸法変化率 (%)								
												変退色	綿											
TD-800	GGN	P52	遮光	3,900	2,600	150	タテ0.0cm×ヨコ0.0cm	A2180351	ポリエステル100%	260	3-4	4-5	4-5	4-5	4-5	タテ-0.2 ヨコ-0.5	2級							
	Y										3-4	4-5	4-5	4-5	4-5		2級							
	GBR										3-4	4-5	4-5	4-5	4-5		2級							
	PI										4	4-5	4-5	4-5	4-5		2級							
	BL										3-4	4-5	4-5	4-5	4-5		2級							
	EM										3-4	4-5	4-5	4-5	4-5		2級							
	GY										4	4-5	4-5	5	5		2級							
	BR										4	4-5	4-5	5	5		2級							
	BE										4	4-5	4-5	5	5		2級							
TD-801	BE/LBE	P57	遮光	6,600	4,400	148	タテ37.5cm×ヨコ37.0cm	A2160560	ポリエステル100%	282	3-4	4-5	5	4-5	5	タテ-0.3 ヨコ0.1	2級(裏地付き TD-805 LBE)							
	BL/DBL										4以上	4-5	4-5	4-5	4-5		1級(裏地付き TD-805 LBE)							
	GRN/GRN										4	4-5	4-5	5	4-5		1級(裏地付き TD-805 LBE)							
TD-802	BE/LBE	P58	遮光	6,600	4,400	148	タテ45.0cm×ヨコ37.0cm	A2160535	ポリエステル100%	230	4以上	4-5	5	4-5	5	タテ-0.8 ヨコ-0.3	2級(裏地付き TD-805 LBE)							
	DBR/BR										4以上	4-5	4-5	5	4-5		2級(裏地付き TD-805 LBE)							
	GRN/GRN										4以上	4-5	4-5	5	4-5		1級(裏地付き TD-805 LBE)							
TD-805	LBE	P48	遮光	2,700	1,800	150	タテ0.0cm×ヨコ0.0cm	A2160686	ポリエステル100%	185	4以上	4-5	5	4-5	5	タテ-0.3 ヨコ0.2	3級							
	BE										4	4-5	5	4-5	5		3級							
	BL										4	4-5	5	4-5	5		2級							
	BR										3-4	4-5	4-5	4-5	5		1級							
	OR										4	4-5	5	4-5	5		2級							
	DBL										3-4	4-5	4-5	4-5	5		1級							
	GRN										4	4-5	4-5	4-5	5		2級							
TD-806	LBE	P46	遮光	4,900	3,260	150	タテ0.0cm×ヨコ0.0cm	A2180239	ポリエステル100%	345	3-4	4-5	4-5	4-5	4-5	タテ-0.5 ヨコ-0.5	3級							
	PGY										3-4	4-5	4-5	4-5	4-5		3級							
	LY										3-4	4-5	4-5	4-5	4-5		3級							
	DBL										3-4	4-5	4-5	4-5	4-5		2級							
	MGY										3	4-5	4-5	4-5	4-5		2級							
	TC										3-4	4-5	4-5	4-5	4-5		2級							
	MUS										3-4	4-5	4-5	4-5	4-5		3級							
	Y										3-4	4-5	4-5	4-5	4-5		3級							
	LOV										3-4	4-5	4-5	4-5	4-5		3級							
	GRN										3-4	4-5	4-5	4-5	4-5		3級							
	TD-807					LGY	P50	遮光	3,900	2,600	150	タテ0.0cm×ヨコ0.0cm	A2180240	ポリエステル100%	310	3-4	4		4-5	4-5	4-5	タテ-0.7 ヨコ-0.3	3級	
						GY										3-4	4-5		4-5	4-5	4-5		3級	
						BE										3-4	4-5		4-5	4-5	4-5		3級	
						PI										3-4	4-5		4-5	4-5	4-5		3級	
						TC										4	4-5		4-5	4-5	4-5		2級	
						OCH										3-4	4-5		4-5	4-5	4-5		3級	
						MAS										4	4-5		4-5	4-5	4-5		3級	
						YG										4	4-5		4-5	4-5	4-5		3級	
						GN										4	4-5		4-5	4-5	4-5		2級	
						EM										4	4-5		4-5	4-5	4-5		2級	
TPC-601	OR/OR	P54	遮光	6,600	4,400	150	タテ75.0cm×ヨコ50.0cm	A2160498	ポリエステル100%	240	4以上	4-5	4-5	4-5	5	タテ0.0 ヨコ0.1	2級(裏地付き TD-805 LBE)							
	BL/BR										4以上	4-5	5	4-5	5		2級(裏地付き TD-805 LBE)							
TPC-602	OR/OR	P56	遮光	6,600	4,400	150	タテ60.0cm×ヨコ75.0cm	A2160498	ポリエステル100%	240	4以上	4-5	5	4-5	5	タテ-0.1 ヨコ0.1	2級(裏地付き TD-805 LBE)							
	BL/BL										4以上	4-5	5	4-5	5		2級(裏地付き TD-805 LBE)							
TPC-603	MUL/BR	P60	遮光	6,600	4,400	150	タテ75.0cm×ヨコ150.0cm	A2160498	ポリエステル100%	240	4以上	4-5	5	4-5	5	タテ-0.2 ヨコ0.0	2級(裏地付き TD-805 LBE)							
	CHI/BE										4以上	4-5	5	4-5	5		2級(裏地付き TD-805 LBE)							
TPC-604	CHI/BR	P59	遮光	6,600	4,400	150	タテ75.0cm×ヨコ150.0cm	A2160498	ポリエステル100%	240	4	4-5	4-5	4-5	4-5	タテ0.0 ヨコ0.3	2級(裏地付き TD-805 LBE)							
TPC-605	BL	P42	遮光	5,900	3,950	150	タテ61.0cm×ヨコ147.0cm	A2180239	ポリエステル100%	345	3-4	4-5	4-5	4-5	4-5	タテ-0.5 ヨコ-0.5	3級							
TPC-606	CHI	P44	遮光	5,900	3,950	147	タテ61.0cm×ヨコ147.0cm	A2180239	ポリエステル100%	345	4	4	4-5	4-5	4-5	タテ-0.5 ヨコ-0.5	3級							
TPC-607	BR	P45	遮光	4,900	3,260	150	タテ74.0cm×ヨコ74.0cm	A2180240	ポリエステル100%	200	4	4-5	4-5	4-5	4-5	タテ-0.7 ヨコ-0.3	2級							



※耐光堅牢度は色の面(部屋側)からの値で裏(日光)面からの照射では4級です

品番	色記号	ページ	機能	価格 (円/m)	価格 (円/m ²)	有効巾 (cm)	柄リピート	防災認証	組成	重量 (g/m ²)	堅牢度	洗濯		ドライクリーニング A-1法		ウォッシュブル	赤外線カット率 IR (%)	紫外線カット率 UV (%)	洗濯表示
											耐光	洗濯	汚染	変退色	汚染	寸法変化率 (%)			
												変退色	綿						
TW-103	W	P65		2,200	1,480	150	タテ0.0cm×ヨコ0.0cm	A0100412	ポリエステル100%	48	4	4-5	5	4-5	5	タテ0.0 ヨコ-0.3	37.8	65.3	
TW-106	W	P64		2,200	1,480	150	タテ0.0cm×ヨコ0.0cm	A0090399	ポリエステル100%	130	4以上	4-5	4-5	—	—	タテ-1.8 ヨコ-0.6	36.9	56.0	
TW-107	W	P67		3,200	1,060	300	タテ0.0cm×ヨコ1.3cm	A0100005	ポリエステル100%	114	4以上	4-5	5	4-5	5	タテ-0.1 ヨコ-0.3	37.4	57.9	
TW-108	W	P64		2,200	1,480	150	タテ0.0cm×ヨコ0.0cm	A0100006	ポリエステル100%	97	4以上	4-5	5	—	—	タテ-1.7 ヨコ-1.5	40.5	62.3	
TW-109	W	P66		3,200	1,060	300	タテ0.0cm×ヨコ0.0cm	A0100188	ポリエステル100%	38	4以上	4-5	4-5	—	—	タテ-0.5 ヨコ-0.5	36.4	55.9	
TW-116	W	P63		1,600	1,060	150	タテ0.0cm×ヨコ0.0cm	A2180295	ポリエステル100%	100	4	4-5	5	4-5	5	タテ-0.8 ヨコ-1.2	20.3	35.0	
TW-117	W	P62		1,600	1,060	150	タテ0.0cm×ヨコ0.0cm	A2180296	ポリエステル100%	122	4	4-5	5	4-5	5	タテ-0.5 ヨコ-0.5	53.8	80.9	
TW-118	W	P62		1,600	1,060	150	タテ0.0cm×ヨコ0.0cm	A2180297	ポリエステル100%	118	4	4-5	5	4-5	5	タテ-0.5 ヨコ-1.2	73.9	73.9	

※耐光堅牢度は色の面(部屋側)からの値で裏(日光)面からの照射では4級です