

名称	品番	色記号	ページ	機能	価格 (円/m)	価格 (円/m ²)	有効巾 (cm)	柄リピート	防災認証	組成	重量 (g/m ²)	堅牢度 耐光	洗濯		ドライクリーニング A-1法		ウオッシュャブル 寸法変化率 (%)	赤外線カット 率 IR (%)	紫外線カット 率 UV (%)	洗濯表示
													洗濯 変退色	汚染 綿	変退色	汚染				
																	4以上	4-5	4-5	
アズーラ・ポイル	TPS-703	BL	P6	masa	5,800	3,860	150	タテ61.0cm×ヨコ147.0cm	A2180342	ポリエステル100%	68	3-4	4-5	4-5	4-5	4-5	タテ-0.8 ヨコ-0.5	66.6	73.6	
レジャー・ポイル	TPS-704	CHI	P4	masa	5,800	3,860	150	タテ61.0cm×ヨコ147.0cm	A2180342	ポリエステル100%	68	4	4	4-5	4-5	4-5	タテ-0.8 ヨコ-0.5	67.8	74.1	
コカゲ	TBO-002	OR	P19	masa	7,100	4,730	150	タテ31.0cm×ヨコ25.0cm	A2120180	ポリエステル100%	48	4以上	4-5	4-5	4-5	4-5	タテ-0.8 ヨコ-0.4	58.7	68.7	
		LGRN										4以上	4-5	4-5	4-5	4-5		60.8	69.3	
		NA										4以上	4-5	4-5	4-5	4-5		61.5	66.1	
ミナモ	TBO-003	R	P16	masa	7,100	4,730	150	タテ62.0cm×ヨコ75.0cm	A2120180	ポリエステル100%	45	4以上	4-5	4-5	4-5	4-5	タテ-0.4 ヨコ-0.2	54.6	61.7	
		BE										4以上	4-5	4-5	4-5	4-5		53.7	60.2	
		NA										4以上	4-5	4-5	4-5	4-5		55.2	60.3	
ヒビキ	TBO-005	LGY	P21	masa	7,100	4,730	150	タテ30.0cm×ヨコ25.0cm	A2120180	ポリエステル100%	45	4以上	4-5	5	5	5	タテ-0.7 ヨコ-0.0	60.0	63.3	
		OR										4以上	4-5	4-5	5	5		63.9	71.6	
		BK										4以上	4-5	4-5	5	4-5		67.2	74.2	
マユ	TBO-006	LGY	P17	masa	7,100	4,730	150	タテ30.0cm×ヨコ12.5cm	A2120180	ポリエステル100%	42	4以上	4-5	5	5	5	タテ-0.8 ヨコ-0.2	56.6	63.1	
		GO										4	4-5	4-5	5	5		59.8	66.7	
		BR										4	4-5	4-5	5	5		60.2	70.4	
サラサ	TBO-007	LGY	P18	masa	7,100	4,730	150	タテ15.0cm×ヨコ25.0cm	A2120180	ポリエステル100%	33	4以上	4-5	5	4-5	5	タテ-0.5 ヨコ-0.2	46.9	52.4	
		R										4	4-5	4-5	5	5		50.5	59.8	
		GRN										4以上	4-5	4-5	5	5		50.6	56.9	
エダブリ	TBO-008	LGY	P20	masa	7,100	4,730	150	タテ59.5cm×ヨコ75.0cm	A2120180	ポリエステル100%	49	4	4-5	5	5	5	タテ-0.5 ヨコ-0.3	62.6	69.0	
		GO										4以上	4-5	4-5	5	5		62.6	69.6	
		GRN										4	4-5	4-5	5	5		61.5	69.5	
ナガレ	TBO-009	BE	P22	masa	7,100	4,730	150	タテ30.0cm×ヨコ37.5cm	A2120180	ポリエステル100%	43	4以上	4-5	5	5	5	タテ-0.5 ヨコ-0.3	62.0	69.1	
		BR										4以上	4-5	4-5	5	5		61.1	71.5	
		PUR										4	4-5	4-5	5	5		62.0	70.9	
フォーリ	TBO-010	GRN	P15	masa	7,100	4,730	139	タテ15.5cm×ヨコ15.0cm	A2180294	ポリエステル100%	48	3-4	4-5	4-5	4-5	4-5	タテ-0.3 ヨコ-0.2	68.2	74.8	
		CR										4	4-5	4-5	4-5	4-5		65.6	70.8	
		GY										3	4-5	4-5	4-5	4-5		66.1	71.6	
		LBE										3-4	4-5	4-5	4-5	4-5		68.2	74.7	
		OCH										3-4	4-5	4-5	4-5	4-5		67.0	74.0	
スタンパ	TBO-011	TC	P12	masa	7,100	4,730	147.5	タテ2.0cm×ヨコ3.3cm	A2180294	ポリエステル100%	42	3-4	4-5	4-5	4-5	4-5	タテ-0.7 ヨコ-0.2	69.3	79.9	
		CR										4	4-5	4-5	4-5	4-5		69.3	76.3	
		GY										3-4	4-5	4-5	4-5	4-5		70.1	78.4	
		LOV										3-4	4-5	4-5	4-5	4-5		68.0	75.7	
		MS										3-4	4-5	4-5	4-5	4-5		68.7	78.7	
		LBE										3-4	4-5	4-5	4-5	4-5		67.0	73.0	
ステラ	TBO-012	CR	P10	masa	7,100	4,730	148.5	タテ30.0cm×ヨコ37.0cm	A2180294	ポリエステル100%	48	4	4-5	4-5	4-5	4-5	タテ0.0 ヨコ-0.2	55.0	60.1	
		BL										3-4	4-5	4-5	4-5	4-5		68.9	75.5	
		TC										3-4	4-5	4-5	4-5	4-5		68.3	76.7	
		MS										3	4-5	4-5	4-5	4-5		70.8	78.3	
		LBR										3-4	4-5	4-5	4-5	4-5		74.2	82.4	
ピアヌーラ	TBO-013	CR	P14	masa	7,100	4,730	148	タテ30.0cm×ヨコ74.0cm	A2180294	ポリエステル100%	44	4	4-5	4-5	4-5	4-5	タテ-0.2 ヨコ0.0	74.0	80.2	
		GY										3	4-5	4-5	4-5	4-5		60.9	67.0	
		LBE										3-4	4-5	4-5	4-5	4-5		71.1	76.8	
		GRN										3	4-5	4-5	4-5	4-5		71.1	78.7	
		LBR										3	4-5	4-5	4-5	4-5		71.1	78.7	



バルバラ	TC-006	OR	P25	masa	5,250	3,500	150	タテ0.0cm×ヨコ0.0cm	A0090399	ポリエステル100%	130	4以上	4-5	4-5	—	—	タテ-1.8 ヨコ-0.6	58.4	64.9
		Y										4以上	4-5	4-5	—	—		56.5	62.5
		GRN										4以上	4-5	4-5	—	—		55.6	62.3
		BL										4以上	4-5	4-5	—	—		60.8	67.1
		NA										4以上	5	5	5	5		60.4	65.9
テレーザ	TC-007	IVY	P33	masa	10,500	3,500	300	タテ0.0cm×ヨコ1.3cm	A0100005	ポリエステル100%	114	4以上	4-5	4-5	—	—	タテ-0.3 ヨコ-1.0	53.6	60.1
		PI										4以上	4-5	4-5	—	—		59.8	65.4
		NA										4以上	5	5	5	5		59.7	65.2
ミーナ	TC-008	IVY	P26	masa	5,250	3,500	150	タテ0.0cm×ヨコ0.0cm	A0100006	ポリエステル100%	97	4以上	4-5	5	—	—	タテ-1.7 ヨコ-1.5	60.9	67.8
		Y										4以上	4-5	5	—	—		64.9	72.4
		NA										4以上	4-5	5	5	5		60.8	67.6
ロベルタ	TC-009	GR	P32	masa	9,600	3,200	300	タテ0.0cm×ヨコ0.0cm	A0100188	ポリエステル100%	38	4以上	4-5	4-5	—	—	タテ-0.5 ヨコ-0.5	59.4	64.4
		LY										4以上	4-5	4-5	—	—		52.0	56.3
		OR										4以上	4-5	4-5	—	—		56.8	62.2
		DBR										4以上	4-5	4-5	—	—		49.6	55.6
		NA										4	4-5	5	4-5	5		52.1	56.3
パオラ	TC-010	Y	P23	masa	4,800	3,200	150	タテ0.0cm×ヨコ0.0cm	A0090426	ポリエステル100%	93	4	4-5	5	—	—	タテ-0.7 ヨコ-0.5	47.9	53.4
		LY										4	4-5	5	—	—		49.4	54.6
		DGR										4	4-5	4-5	—	—		46.5	55.0
		DBR										4	4-5	4-5	—	—		51.2	58.4
		NA										4以上	5	5	5	5		47.0	52.7
エヴァ	TC-013	DBR	P29	masa	4,450	2,970	150	タテ0.0cm×ヨコ0.0cm	A2180352	ポリエステル100%	22	4以上	4-5	4-5	—	—	タテ-0.5 ヨコ-1.0	34.8	42.8
		OR										4以上	4-5	4-5	—	—		38.6	43.7
		R										4以上	4-5	4-5	—	—		37.7	42.6
		BK										4以上	4-5	4-5	—	—		38.2	44.3
		NA										4	4-5	5	4-5	5		36.7	40.2
ザラ	TC-014	DGR	P31	masa	10,500	3,500	300	タテ0.0cm×ヨコ0.0cm	A2180357	ポリエステル100%	45	4以上	4-5	4-5	4-5	—	タテ-0.5 ヨコ-0.6	64.9	71.8
		R										4以上	4-5	4-5	4-5	—		53.9	60.4
		DBR										4	4-5	4-5	4-5	—		60.1	68.5
		BE										4	4-5	4-5	4-5	—		61.5	67.3
		NA										—	—	—	—	—		63.6	69.6
ピノ	TC-015	GY	P24	masa	3,500	2,330	140	タテ0.0cm×ヨコ0.0cm	—	ポリエステル100%	32	4以上	4-5	5	4-5	5	タテ-0.0 ヨコ0.3	54.2	61.5
		PN										4以上	4-5	4-5	4-5	4-5		54.2	61.5
		BE										4	4-5	4-5	4-5	4-5		54.2	61.5
		GN										4以上	4-5	4-5	4-5	4-5		54.2	61.5
ボルティ	TC-019	BE	P30	masa	9,800	3,260	300	タテ0.0cm×ヨコ0.0cm	A2210307	ポリエステル100%	166	4以上	4-5	5	4-5	5	タテ-1.0 ヨコ-0.3	61.0	61.2
		BR										4以上	4-5	4-5	4-5	5		56.3	59.8
		NA										4以上	4-5	4-5	4-5	5		57.6	60.0
スコツツェ	TC-020	BE	P27	masa	5,000	3,330	150	タテ0.0cm×ヨコ0.0cm	A2210328	ポリエステル100%	150	4以上	4-5	5	4-5	5	タテ-0.5 ヨコ0.2	61.1	60.4
		GRN										4以上	4-5	5	4-5	5		58.7	64.9
		NA										4以上	4-5	5	4-5	5		60.9	62.7
リネエ	TC-021	BL	P28	masa	5,000	3,330	150	タテ8.5cm×ヨコ8.5cm	A2210329	ポリエステル100%	86	4以上	4-5	4-5	4-5	5	タテ-0.5 ヨコ0.1	59.0	68.8
		LBR										4以上	4-5	4-5	4-5	5		57.9	68.9
		NA										4以上	4-5	5	4-5	5		58.6	62.0
ファピア	TC-022	LGY	P8	masa	4,800	3,200	150	タテ0.0cm×ヨコ0.0cm	A2210362	ポリエステル100%	68	4	4-5	4-5	4-5	4-5	タテ-0.8 ヨコ-0.5	67.8	74.1
		GY										4	4-5	4-5	4-5	4-5		66.9	73.5
		LBE										3-4	4-5	4-5	4-5	4-5		67.1	73.5
		PI										4	4-5	4-5	4-5	4-5		66.4	72.5
		MAS										3-4	4-5	4-5	4-5	4-5		66.5	72.6
		GO										3-4	4-5	4-5	4-5	4-5		66.4	74.3
		EM										3-4	4-5	4-5	4-5	4-5		67.5	75.1
		GN										3-4	4-5	4-5	4-5	4-5		66.0	73.4



※耐光堅牢度は色の面（部屋側）からの値で裏（日光）面からの照射では4級です

名称	品番	色記号	ページ	機能	価格 (円/m)	価格 (円/m ²)	有効巾 (cm)	柄リピート	防災認証	組成	重量 (g/m ²)	堅牢度 耐光	洗濯			ドライクリーニング A-1法		ウォッシュブル 寸法変化率 (%)	遮光等級	洗濯表示
													洗濯	汚染	変退色	汚染				
													変退色	綿						
フォルテ	TD-800	GGN	P46	遮光	3,900	2,600	150	タテ0.0cm×ヨコ0.0cm	A2220029	ポリエステル100%	260	3-4	4-5	4-5	4-5	4-5	タテ-0.2 ヨコ-0.5	2級		
		Y										3-4	4-5	4-5	4-5	4-5		2級		
		GBR										3-4	4-5	4-5	4-5	4-5		2級		
		PI										4	4-5	4-5	4-5	4-5		2級		
		BL										3-4	4-5	4-5	4-5	4-5		2級		
		EM					3-4	4-5	4-5	4-5	4-5	2級								
		GY					150	タテ0.0cm×ヨコ0.0cm	A2210153	ポリエステル100%	260	4	4-5	4-5	5	5	タテ-0.2 ヨコ0.3	2級		
		BR										4	4-5	4-5	5	5		2級		
		BE										4	4-5	4-5	5	5		2級		
GN	4	4-5	4-5	5	5	2級														
ルーチェ	TD-805	LBE	P42	遮光	2,700	1,800	150	タテ0.0cm×ヨコ0.0cm	A2210154	ポリエステル100%	185	4以上	4-5	5	4-5	5	タテ-0.3 ヨコ0.2	3級		
		BE										4	4-5	5	4-5	5		3級		
		BL										4	4-5	5	4-5	5		2級		
		BR										3-4	4-5	4-5	4-5	5		1級		
		OR										4	4-5	5	4-5	5		2級		
		DBL										3-4	4-5	4-5	4-5	5		1級		
		GRN										4	4-5	4-5	4-5	5		2級		
トッカ	TD-806	LBE	P40	遮光	4,900	3,260	150	タテ0.0cm×ヨコ0.0cm	A2210364	ポリエステル100%	345	3-4	4-5	4-5	4-5	4-5	タテ-0.5 ヨコ-0.5	3級		
		PGY										3-4	4-5	4-5	4-5	4-5		3級		
		LY										3-4	4-5	4-5	4-5	4-5		3級		
		DBL										3-4	4-5	4-5	4-5	4-5		2級		
		MGY										3	4-5	4-5	4-5	4-5		2級		
		TC										3-4	4-5	4-5	4-5	4-5		2級		
		MUS										3-4	4-5	4-5	4-5	4-5		3級		
		Y										3-4	4-5	4-5	4-5	4-5		3級		
		LOV										3-4	4-5	4-5	4-5	4-5		3級		
		GRN										3-4	4-5	4-5	4-5	4-5		3級		
		MS					3-4	4-5	4-5	4-5	4-5	3級								
		LMS					3-4	4-5	4-5	4-5	4-5	3級								
		EM					3-4	4-5	4-5	4-5	4-5	3級								
		LGY					4	4-5	5	4-5	5	タテ-0.3 ヨコ0.0	3級							
		BE					4	4-5	5	4-5	5		2級							
		BL					4	4-5	4-5	4-5	5		1級							
		LPI					4	4-5	4-5	4-5	5		2級							
		BR					4以上	4-5	4-5	4-5	5		1級							
		DBR					4以上	4-5	4-5	4-5	4-5		1級							
		サビア					TD-807	LGY	P44	遮光	3,900		2,600	150	タテ0.0cm×ヨコ0.0cm	A2210365	ポリエステル100%	200	3-4	4
GY	3-4		4-5	4-5	4-5	4-5		3級												
BE	3-4		4-5	4-5	4-5	4-5		3級												
PI	3-4		4-5	4-5	4-5	4-5		3級												
TC	4		4-5	4-5	4-5	4-5		2級												
OCH	3-4		4-5	4-5	4-5	4-5		3級												
MAS	4		4-5	4-5	4-5	4-5		3級												
YG	4		4-5	4-5	4-5	4-5		3級												
GN	4		4-5	4-5	4-5	4-5		2級												
EM	4		4-5	4-5	4-5	4-5		2級												
DGY	3		4-5	4-5	4-5	4-5		2級												
BL	3		4-5	4-5	4-5	4-5		2級												
アズーラ	TPC-605		BL	P36	遮光	5,900		3,950				150							タテ61.0cm×ヨコ147.0cm	A2180239
ボラーレ	TPC-606	CHI	P38	遮光	5,900	3,950	147	タテ61.0cm×ヨコ147.0cm	A2180239	ポリエステル100%	345	4	4	4-5	4-5	4-5	タテ-0.5 ヨコ-0.5	3級		
カナール	TPC-607	BR	P39	遮光	4,900	3,260	150	タテ74.0cm×ヨコ74.0cm	A2180240	ポリエステル100%	200	4	4-5	4-5	4-5	4-5	タテ-0.7 ヨコ-0.3	2級		



※耐光堅牢度は色の面（部屋側）からの値で裏（日光）面からの照射では4級です